

1. Description:

Commodity	Material	Standard	Condition
Ti-6Al-4V ELI bar	Ti-6Al-4V ELI	ASTM F136	Annealed
Heat NO.	Lot No.	Size	Weight
MT17617	1709203	dia 4.0x2000mm	29.80Kgs

2. Chemical composition (wt%) :

Element	Ti	N	C	H	Fe	O	Al	V	
Requirements (max.)	Bal	0.05	0.08	0.012	0.25	0.13	5.5-6.5	3.5-4.5	
Results	top	Bal	0.006	0.01	0.001	0.05	0.11	6.23	4.2
	bottom	Bal	/	/	/	0.05	0.12	6.18	4.15

3. Mechanical properties:

Test Items	Tensile strength Rm (MPa)	Yield strength Rp0.2 (MPa)	Elongations (%)
Requirements	>=860	>=795	>=10
Results	980	841	18

4. Other test items:

Microstructure	Ultrasonic	Dimensional Inspection	Visual Inspection	Surface contamination
Qualified	Qualified	Qualified	Qualified	Clean

5. Conclusion and Statement:

We hereby certify that these Titanium plate Ti-6Al-4V ELI herein has been manufactured, samples, tested and inspected in accordance with ASTM F136 and other specified requirements of contract number TG1700068a, and met these requirements.

Inspected by	Prepared by	Approved by
Michele Zhang	Jimmy	Andrew Wang
Sep.18th, 2017.	Sep.18th, 2017.	Sep.18th, 2017.